

Nitto

HYDRANAUTICS
Nitto Group Company

Membrane Element

CPA7-LD (With Low Fouling LD Technology[®])

Performance

Permeate Flow:	11,500 gpd (43.5 m ³ /d)
Salt Rejection:	99.8% (99.7% minimum)

Type

Configuration:	Low Fouling Spiral Wound
Membrane Polymer:	Composite Polyamide
Membrane Active Area:	400 ft ² (37.2 m ²)
Feed Spacer:	34 mil (0.864 mm)

Application Data*

Maximum Applied Pressure:	600 psig (4.14 MPa)
Maximum Chlorine Concentration:	< 0.1 ppm
Maximum Operating Temperature:	113 °F (45 °C)
pH Range, Continuous (Cleaning):	2–11 (1–13)*
Maximum Feedwater Turbidity:	1.0 NTU
Maximum Feedwater SDI (15 mins.):	5.0
Maximum Feed Flow:	75 gpm (17.0 m ³ /h)
Maximum Pressure Drop for Each Element:	15 psi


*Limitations shown here are for general use. For specific projects, operating at more conservative values may ensure the best performance and longest life of the membrane. See Hydranautics Technical Service Bulletin TSB107 for more details on operation limits, cleaning pH, and cleaning temperatures.

Test Conditions

The stated performance is initial (data taken after 30 minutes of operation), based on the following conditions:

1500 ppm NaCl solution
225 psi (1.55 MPa) Applied Pressure
77 °F (25 °C) Operating Temperature
15% Permeate Recovery
6.5–7.0 pH Range

Product Dimensions



A, inches (mm)	B, inches (mm)	C, inches (mm)	Weight, lbs. (kgs.)
40.0 (1016)	7.89 (200)	1.125 (28.6)	33 (15)

Notice: Permeate flow for individual elements may vary ± 15 percent. Membrane active area may vary ± 4 %. All membrane elements are supplied with a brine seal, interconnector, and o-rings. Elements are enclosed in a sealed polyethylene bag containing less than 1.0% sodium meta-bisulfite solution, and then packaged in a cardboard box.

Hydranautics believes the information and data contained herein to be accurate and useful. The information and data are offered in good faith, but without guarantee, as conditions and methods of use of our products are beyond our control. Hydranautics assumes no liability for results obtained or damages incurred through the application of the presented information and data. It is the user's responsibility to determine the appropriateness of Hydranautics' products for the user's specific end uses.

8/29/16